SOME LIKE IT HOT

HEAT TOLERANT VRLA BATTERIES

T7500E

- Helios[™] Additive reduces float current up to 75% enhancing high temperature life
- THT[™] Plastic specifically formulated heat resistant plastic case and cover optimizes compression
- Microcat® Catalyst lowers float current, mitigates thermal buildup and cell dryout
- **■** Exclusive IPF® Technology optimizes power capacity, cell consistency, and long-term reliability
- TempX[™] Alloy inhibits corrosion under the highest temperature extremes
- Advanced AGM technology for superior high rate, short term power
- Front access design for easy installation and maintenance
- Reinforced case resists bulging and meets safety requirements (UL 94 V-0)
- Case & cover heat sealed and 100% tested to prevent leaks
- Epoxy-sealed posts eliminate leaks
- Puncture resistant micro-porous glass mat separators
- Flame arresting, low pressure, self-sealing valves are 100% factory tested
- Computer-aided design and manufacturing control processes and standards to ensure quality products
- All batteries meet or exceed IEEE recommended practices
- Battery design and construction meet UL recognition requirements

SPECIFICATIONS

Nominal Voltage: 12-Volt/750 w.p.c.

@ 15 min. rate to 1.67 v.p.c.

Positive Plate: Pure lead, low-calcium, high-tin alloy

Negative Plate: Lead calcium alloy Post Seal: Epoxy-sealed

Terminal: Front access, 1/4" - 20 threaded insert

Container: Flame-retardant, UL 94 V-0/39% L.O.I.

Catalyst: Microcat®

Safety Vent: Low positive pressure,

self-sealing w/ flame arrestor

Float Voltage: 2.25 v.p.c. ± 0.01 v.p.c. (Range: 13.44

to 13.56 volts per 6-cell battery)

ISO 14001


Battery Warranty: 5 years in float applications at 95°F (35°C)

Weight: 151 lbs. (68.5 kg)

DISCHARGE RATINGS IN WATTS DER CELL @ 77°F (25°C)†

DISCHARGE RATINGS IN WAITS PER CELL @ 77 F (25 C)								
Volts Per Cell (VPC)	5 MINS.	10 MINS.	15 MINS.	20 MINS.	30 MINS.	40 MINS.	50 MINS.	60 MINS.
1.60	1181	958	794	668	499	398	333	287
1.67	1086	891	750	641	488	393	330	285
1.70	1038	857	724	622	480	389	328	283
1.75	951	787	669	580	457	377	320	278
1.80	839	704	604	528	423	353	304	267

Subject to change without notice.



OPTIONAL FACTORY ACCEPTANCE TESTING

- · More economical than performing a load test on site
- · Confirms published capacity rating of product
- Establishes a factory baseline ohmic reading
- Formal test report provided
- Contact your East Penn Mfg. representative for additional information

TESTING SPECIFICTIONS

- Exceeds IEEE-1188 standards
- 15 minute battery rate to 1.67 vpc
- · Constant current discharge
- String > 100% capacity All individual batteries ≥ 95% capacity
- Conductance readings taken before the test
- Battery voltage recorded on report every 2.5 minutes





